

CARATTERISTICHE TECNICHE

Technical specifications

Norma Standard	Caratteristiche Features	Valori Prescritti Value Required	Polignano
ISO 10545/3	Assorbimento d'acqua Water absorption	≤3%	0,5% surface 4% global
ASTM C373	Assorbimento d'acqua Water absorption	≤3%	0,5% surface 4% global
ISO 10545/9	Resistenza agli sbalzi termici Thermal shock	Nessuna alterazione visibile No visible alteration	Conforme According to
ASTM C484	Thermal shock	Unaffected	Unaffected
ISO 10545/13	Resistenza agli attacchi chimici Chemical Resistance	Nessuna alterazione visibile No visible alteration	Resiste Resistant
ASTM C650	Chemical Resistance	No visible alteration	Unaffected
UNE-ENV12633:2003	Resistenza allo scivolamento (R) Slip Resistance classification (R)		R10
UNE-ENV12633:2006	Resistenza allo scivolamento (CL) Slip Resistance classification (CL)		CLASSE 3 Rd>45
ANSI A326.3:2022	Determination of Dynamic Coefficient of Friction (DCOF)	Before 0,30 After 0,29	Before 0,50 After 0,50
LEED CERTIFICATION	Contenuto argilla riciclata (% preconsumer) Recycled clay content (% preconsumer)		50 % tutti gli articoli 50% all items

PACKING

Formato Size	Pcs Sqm	Box Pallet	Pcs Box	Sqm Box	Kg Box	Kg Pallet	Sqm Pallet
Puntinato	39	56	30	0,77	15,80	898,30	43,12
Base	39	56	30	0,77	15,80	898,30	43,12

Classificazione secondo lo standard UNI EN 87: Group AI-AIIa
Metodo di formatura e grado di assorbimento d'acqua 0<AI-AIIa≤6%

*Classification in accordance with standard UNI EN 87: Group AI-AIIa
Shaping method extrusion with water absorption 0<AI-AIIa≤6%*